

## Flammability Report

CAR	JC	Supplier : LG HAUSYS	
PART NO.			
PART NAME	Artificial Leather 'D' Grade		
Color	MCH	Judgement	(Pass) . Fail
Thickness	1.0T	Remarks	
Standard	FMVSS 302		
Specimens	100mm * 350mm		
		Manu. Date	2010.11.28

Condition Of Specimens	Constant Temp. Condition	High Temp. Condition
Date	2010.12.01	2010.12.01
Temp.	21 °C	80 °C
Humidity	55%	55%
Hour	24HR	168hrs

Condition Of Specimens	Condition 21±5.4 °C , 55±	High Temp. Condition
Date	2010.12.01	2010.12.01
Temp.	21 °C	80 °C
Humidity	55%	55%
Hour	24HR	168hrs

D	NO.	Constant Temp. Condition			High Temp. Condition				
		Distance (mm)	Time (sec)	Speed (mm/min)	Distance (mm)	Time (sec)	Speed (mm/min)		
L	1	0	0	S.E	Max 0	0	0	S.E	Max 0
	2	0	0	S.E		0	0	S.E	
	3	0	0	S.E		0	0	S.E	
	4	0	0	S.E		0	0	S.E	
	5	0	0	S.E		0	0	S.E	
W	1	0	0	S.E	Ave. SE	0	0	S.E	Ave. SE
	2	0	0	S.E		0	0	S.E	
	3	0	0	S.E		0	0	S.E	
	4	0	0	S.E		0	0	S.E	
	5	0	0	S.E		0	0	S.E	
Judgement		(Pass) . Fail			(Pass) . Fail				



Ulsan Complex Lab.



## Flammability Report

CAR	JC	Supplier : LG HAUSYS	
PART NO.			
PART NAME	Artificial Leather 'D' Grade		
Color	WBR	Judgement	(Pass) . Fail
Thickness	1.0T	Remarks	
Standard	FMVSS 302		
Specimens	100mm * 350mm		
		Manu. Date	2011.02.18

Condition Of Specimens	Constant Temp. Condition	High Temp. Condition
Date	2011.02.20	2011.02.20
Temp.	21 °C	80 °C
Humidity	55%	55%
Hour	24HR	168hrs

Condition Of Specimens	Condition 21±5.4 °C , 55±	High Temp. Condition
Date	2011.02.20	2011.02.20
Temp.	21 °C	80 °C
Humidity	55%	55%
Hour	24HR	168hrs

D	NO.	Constant Temp. Condition			High Temp. Condition				
		Distance (mm)	Time (sec)	Speed (mm/min)	Distance (mm)	Time (sec)	Speed (mm/min)		
L	1	0	0	S.E	Max 0	0	0	S.E	Max 0
	2	0	0	S.E		0	0	S.E	
	3	0	0	S.E		0	0	S.E	
	4	0	0	S.E		0	0	S.E	
	5	0	0	S.E		0	0	S.E	
W	1	0	0	S.E	Ave. SE	0	0	S.E	Ave. SE
	2	0	0	S.E		0	0	S.E	
	3	0	0	S.E		0	0	S.E	
	4	0	0	S.E		0	0	S.E	
	5	0	0	S.E		0	0	S.E	
Judgement		(Pass) . Fail			(Pass) . Fail				



Ulsan Complex Lab.



## Flammability Report

CAR	JC	Supplier : LG HAUSYS	
PART NO.			
PART NAME	Artificial Leather 'D' Grade		
Color	EQ	Judgement	(Pass) . Fail
Thickness	1.0T	Remarks	
Standard	FMVSS 302		
Specimens	100mm * 350mm		
		Manu. Date	2011.04.15

Condition Of Specimens	Constant Temp. Condition	High Temp. Condition
Date	2011.04.18	2011.04.18
Temp.	21 °C	80 °C
Humidity	55%	55%
Hour	24HR	168hrs

Condition Of Specimens	Condition 21±5.4 °C , 55±	High Temp. Condition
Date	2011.04.18	2011.04.18
Temp.	21 °C	80 °C
Humidity	55%	55%
Hour	24HR	168hrs

D	NO.	Constant Temp. Condition			High Temp. Condition				
		Distance (mm)	Time (sec)	Speed (mm/min)	Distance (mm)	Time (sec)	Speed (mm/min)		
L	1	0	0	S.E	Max 0	0	0	S.E	Max 0
	2	0	0	S.E		0	0	S.E	
	3	0	0	S.E		0	0	S.E	
	4	0	0	S.E		0	0	S.E	
	5	0	0	S.E		0	0	S.E	
W	1	0	0	S.E	Ave. SE	0	0	S.E	Ave. SE
	2	0	0	S.E		0	0	S.E	
	3	0	0	S.E		0	0	S.E	
	4	0	0	S.E		0	0	S.E	
	5	0	0	S.E		0	0	S.E	
Judgement		(Pass) . Fail			(Pass) . Fail				



Ulsan Complex Lab.

